




05500 - SPAT-O-RAPID




Ready for use



By spatula:
2-3 coats



Drying time
1-3 hours at 20°C



P500-600

DESCRIPTION

Knifing nitroacrylic putty in tube.

USE

Spot putty used on nitrocombi and thermoplastic old films. Used also on large surfaces by thin layers.

CHARACTERISTICS

- Good filling power
- Shrinkage free
- Easy to apply
- Easy to sand
- No puttying marks when the top coat is over applied

SUBSTRATE PREPARATION

Old paintings

Degrease with 00695 SOLVENTE ANTISILICONE SLOW

Sanded substrates

Apply directly

APPLICATION

Knifing application: by thin layers
The product is ready for use
Flash-off between coats: 20' at 20°C
Film thickness: 150 - 200 µ

DRYING TIME

Air drying at 20°C

For thin layers: 1 hour after the last knifing
For thick layers: on average 3 hours from the last knifing.

APPLICATION

Wet sanding:

P500 grit paper for solid colour finishes.
P600 grit paper for two-coat metallic finishes.



OVERCOATINGS

Any top coat within the Lechler car refinishing range can be applied over this product.

DATA SHEET N° 0313-GB
UP DATED 05/2004

The information shown in these sheets is given in good faith as being true and although every effort of verification has been made before use, we cannot accept responsibility for any inaccuracy. THIS PRODUCT IS FOR THE PROFESSIONAL PAINTING OF ROAD VEHICLES BY QUALIFIED PERSONNEL